

## DOMOLAM FRIGO PANELS - PF

### DESCRIPTION:

The products DOMOLAM **PF** are self-supporting double skin metal faced insulating panels, which are factory manufactured from two metal sheets joined together with polyurethane foam.



CODE / ΚΩΔ.: PF-LC

### APPLICATION SCOPE:

The products are used for the covering of external and internal walls, as well as ceilings at cold storage premises, providing water and air tightness and thermal insulation.



CODE / ΚΩΔ.: PF-F

### QUALITY:

Products are submitted to tests according to the EN 14509:2013.



### ENVIRONMENTAL PROTECTION:

The PIR foam consists of closed cells, is chemically neutral, non toxic, and is produced from environmentally friendly technology with N-Pentane as blow agent without the use of CFC, HCFC.



### TECHNICAL CHARACTERISTICS:

**PF** – The loads calculated are the necessities to obtain the max deformation in mm [span\*10] according to EN14509

Panel thickness (mm)	Metal sheet thickness (mm)	Weight (kg/m <sup>2</sup> )	U-Value (W/m <sup>2</sup> K)	Span (m)	Single span							
					1,5	2,0	2,5	3,0	3,5	4,0	4,5	5,0
50	0,50-0,50	10,39	0,43	q (kN/m <sup>2</sup> )	5,06	2,47	1,35	0,80	0,50	0,32	0,22	0,15
80		11,65	0,27		7,10	3,56	2,00	1,21	0,77	0,51	0,35	0,25
100		12,53	0,22		9,16	4,70	2,70	1,67	1,08	0,73	0,51	0,36
120		13,38	0,18		11,2	5,83	3,40	2,13	1,40	0,96	0,67	0,49
150		14,67	0,14		14,3	7,55	4,47	2,84	1,90	1,32	0,94	0,69
180		15,89	0,12		17,4	9,28	5,56	3,58	2,42	1,70	1,22	0,90
200		16,74	0,11		19,6	10,46	6,26	4,03	2,72	1,91	1,38	1,02

## DECLARATION OF PERFORMANCE No.2/PIR/FRIGO

- |   |   |
|---|---|
| 1. Unique identification code of the product-type:  | DOMOLAM PIR PF  |
| 2. Type, batch or serial number or any other element allowing identification of the construction product as required pursuant to Article 11(4):             | PF-LC, PF-F   |
| 3. Intended use or uses of the construction product, in accordance with the applicable harmonised technical specification, as foreseen by the manufacturer: | Self supporting double skin metal faced insulating panels – External or internal walls & ceilings |
| 4. Name, registered trade name or registered trade mark and contact address of the manufacturer as required pursuant to Article 11(5):                      | PAGOUNI S.A., 57008 Echedoros, Thessaloniki, Greece   |
| 5. Where applicable, name and contact address of the authorised representative whose mandate covers the tasks specified in Article 12(2):                   | Not relevant  |
| 6. System or systems of assessment and verification of constancy of performance of the construction product as set out in Annex V:                          | AVCP – System 1   |
| 7. In case of the declaration of performance concerning a construction product covered by a harmonised standard:  | CSI SPA No. 497 – EN 14509  |
| 8. In case of the declaration of performance concerning a construction product for which a European Technical Assessment has been issued:                   | Not relevant  |

9. Declared performance

Essential characteristics	Performance	Harmonized technical specification
External pre-painted galvanized steel	S280+Z140	EN 10346
Internal pre-painted galvanized steel	S280+Z140	
<b>Thickness in mm</b>	50,80,100,120,150,180,200	EN 14509
External pre-painted galvanized steel thickness	0,40; 0,45; 0,50; 0,55	EN 10143
Internal pre-painted galvanized steel thickness	0,40; 0,45; 0,50; 0,55	
External coating (µm)	Standard Polyester 20+5	EN 10169
Internal coating (µm)		
Density (kg/m <sup>3</sup> )	45	EN 1602

<b>Thermal conductivity (W/mK)</b>	0,0215		EN 13165
<b>Thermal transmittance (W/m<sup>2</sup>K)</b>	<b>Thickness</b>	<b>U - Value</b>	EN ISO 10456
	50	0,43	
	80	0,27	
	100	0,22	
	120	0,18	
	150	0,14	
	180	0,12	
	200	0,11	

<b>Reaction to fire</b>	B-s2-d0		EN 13501-1
<b>Resistance to fire</b>	<b>Thickness</b>	<b>Resistance</b>	EN 13501-2
	50	NPD	
	80		
	100	E 30	
	120		
	150	E 45	
	180	E 90	
	200		

Water permeability	Class A	EN 12865
Water vapour permeability	Impermeable	EN 14509
Air permeability	0,14 m <sup>3</sup> /m <sup>2</sup> /h at 50 Pa	EN 12114
Airborne sound insulation Rw (dB)	25	EN ISO 717-1
Sound absorption a <sub>w</sub>	0,10	EN ISO 11654
Durability	Pass	EN 14509

#### Mechanical resistance

Tensile strength (MPa)	0,13		EN 14509
Compressive strength (MPa)	0,12		
Shear strength (MPa)	0,10		
Shear modulus (MPa)	2,80		
Wrinkling stress (external face) panel thickness	<b>100</b>	<b>180</b>	
- in span (MPa)	140	100	
- in span, elevated temperature (MPa)	134	95	
- at central support (MPa)	129	90	
- at central support, elevated temperature (MPa)	127	85	
Wrinkling stress (internal face) panel thickness	<b>100</b>	<b>180</b>	
- in span (MPa)	110	74	
- at central support (MPa)	95	70	

10. The performance of the product identified in points 1 and 2 is in conformity with the declared performance in point 9.

This declaration of performance is issued under the sole responsibility of the manufacturer identified in point 4.

Signed for and on behalf of the manufacturer by:



Vrellas Charisis - Quality Engineer of Pagouni SA

Thessaloniki 15.06.2016